

PRODUCT INFORMATION
OKULEN® 500 - red - FN3000

OKULEN® 500 is a high molecular low pressure polyethylene with a molecular weight of approx. 500.000 g/mol. (HMW-PE)

Properties:

- EU1935/2004 - conform
- EU10/2011 - conform
- FDA - conform

Colour:

red FN3000 / simillar RAL 3020

Range ofapplications:

- Food industry

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein
Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.come-mail: info@okulen.com

PRODUCT INFORMATION
OKULEN® 500 - red - FN3000

Characteristics and standard values

Properties	Method	OKULEN® 500 - red - FN3000	
		SI	US
Physical properties			
Molecular-weight	k.a.	~ 0.5 Mio. g/mol.	~ 0.5 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.950 g/cm ³	> 59.306 lb/ft ³
Notched impact strength	DINENISO 21304-2 (04/2021)	> 15 kJ/m ²	> 7.1325 ft-lb/in ²
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	360 - 440	360 - 440
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 26 N/mm ²	> 3770 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 350 %	> 350 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 1000 N/mm ²	> 145000 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.15 - 0.22	~ 0.15 - 0.22
Dynamic Friction	ASTM D 1894 (2014)	~ 0.10 - 0.15	~ 0.10 - 0.15
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	65 - 70 D	65 - 70 D
Ball indentation hardness	DINENISO 2039	~ 50 N/mm ²	~ 7250 psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
Thermal properties			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	133 - 136 °C	271.4 - 276.8 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft ² -°F
Max. operation temperature	Literature	80 °C	176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~0.00015 - 0.00020 mm/mm °C	~0.000083 - 0.000111 in/in °F
Electrical properties			
Volume resistivity	DINEN 62631-3-1 (01/2017)	> 1.0E+14 Ohm*cm	> 1.0E+14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	> 1.0E+13 Ohm	> 1.0E+13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
Burning properties			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
Physiological properties			
Food compliant		EU/FDA	EU/FDA

The above data are based on the present knowledge and are given without guarantee. Existing laws and conditions are to be respected by the user of our products. The decision about the suitability of a material for a certain application must be made by the user. We reserve the right to alter the indicated data. The indicated values are for a 15 mm thick sheet, unannealed. Black sheets may have antistatic properties.